
















REVESTIMENTO DE PASTA BRANCA | Norma: EN 14411 - Grupo BIII (GL)

White body wall tiles | Norm: EN 14411 - Group BIII (GL)
 Faïence en pâte blanche | Norme: EN 14411 - Groupe BIII (GL)
 Weißscherbige Wandfliesen | Norm: EN 14411 - Gruppe BIII (GL)

	CARACTERÍSTICAS TÉCNICAS Technical Characteristics Caractéristiques Techniques Technische Merkmale	NORMA DE ENSAIO Testing Standard Norme D'Essai Prüfnorm	REQUISITO Requirement Condition Anforderung	VALOR REZER Recer Value Valeur Recer Recer Wert
	Comprimento e largura Length and width Longuer et larger Länge und Breite - Desvio para a dimensão de fabrico (%) Deviation for manufacturing size (%) Détournement pour la dimension de fabrication (%) Abweichung von Werkmaß (%)	ISO10545-2	±0,50%	CONFORME Compliant Conforme Konform
	Espessura Thickness Épaisseur Dicke - Desvio para a dimensão de fabrico (%) Deviation for manufacturing size (%) Détournement pour la fabrication (%) Abweichung von Werkmaß (%)	ISO10545-2	±10%	CONFORME Compliant Conforme Konform
	Rectilinearidade Rectilinearity Forme Rectiligne Gradheit der Kanten - Desvio para a dimensão de fabrico (%) Deviation for manufacturing size (%) Détournement pour la dimension de fabrication (%) Abweichung von Werkmaß (%)	ISO10545-2	±0,3%	CONFORME Compliant Conforme Konform
	Ortogonalidade Rectangularity Angularité Rechtwinkligkeit - Desvio para a dimensão de fabrico (%) Deviation for manufacturing size (%) Détournement pour la dimension de fabrication (%) Abweichung von Werkmaß (%)	ISO10545-2	±0,5%	CONFORME Compliant Conforme Konform
	Planaridade Flatness Surface Plane Ebenföchigkeit - Empeno central, desvio para a diagonal calculada para a dimensão de fabrico (%) Central warping, diagonal deviation calculated for manufacturing size (%) Entrave centrale, détournement pour la diagonale calculée pour la dimension de la fabrication (%) Mittelpunktswöbung, bezogen auf die vom Werkmaß berechnete Diagonale (%) - Empeno lateral, desvio para a dimensão de fabrico (%) Lateral warping, deviation for manufacturing size (%) Entrave latérale, détournement pour la dimension de fabrication (%) Kantenwöbung, bezogen auf das entsprechende Werkmaß (%) - Empeno pontas, desvio para a diagonal, calculada para a dimensão de fabrico (%) End warping, diagonal deviation, calculated for manufactured size (%) Entrave bouts, détournement pour la dimension de fabrication (%) Windschiefe, bezogen auf die vom Werkmaß berechnete Diagonale (%)	ISO10545-2	-0,3% a +0,5%	CONFORME Compliant Conforme Konform
	Qualidade da superfície Surface quality Qualité superficielle Oberfläche fehlerfrei	ISO10545-2	95% sem defeitos Defect Free Sans Défauts Fehlerfrei	CONFORME Compliant Conforme Konform
	Absorção de Água Water Absorption Absorption d'eau Wasseraufnahme	ISO10545-3	> 10%	CONFORME Compliant Conforme Konform
	Resistência à Flexão Resistance to Bending Résistance à la Flexion Biegefestigkeit - Força de ruptura [N] - Espessura ≥ 7,5mm [S] Breaking strength [N] - Thickness ≥ 7,5mm [S] Force de rupture [N] - Épaisseur ≥ 7,5mm [S] Bruchlast [N] - Dicke ≥ 7,5mm [S] - Força de ruptura [N] - Espessura < 7,5mm [S] Breaking strength [N] - Thickness < 7,5mm [S] Force de rupture [N] - Épaisseur < 7,5mm [S] Bruchlast [N] - Dicke < 7,5mm [S] - Módulo de ruptura [N/mm ²] [R] Modulus of rupture [N/mm ²] [R] Résistance à la flexion [N/mm ²] [R] Biegefestigkeit [N/mm ²] [R]	ISO10545-4	≥ 600 ≥ 200 ≥ 12 ≥ 15	CONFORME Compliant Conforme Konform
	Resistência às Manchas Resistance to Staining Résistance aux taches Fleckenbeständigkeit - Ladrilhos vidrados Glazed tiles Carreaux émaillés Glasierte Fliesen	ISO10545-14	Min. Classe 3 Min. Class 3 Min. Classe 3 Mind. Klasse 3	CONFORME Compliant Conforme Konform
	Resistência aos Químicos Chemical Resistance Résistance aux produits chimiques Chemische Beständigkeit - Resistência aos ácidos e bases baixas concentrações Resistance to low concentrations of acids and alkalis Résistance aux acides et aux bases faibles concentrations Beständigkeit gegen schwach konzentrierte Säuren und Basen - Resistência aos ácidos e bases altas concentrações Resistance to high concentrations of acids and alkalis Résistance aux concentrations élevées d'acides et bases Beständigkeit gegen hoch konzentrierte Säuren und Basen - Resistência aos produtos químicos de limpeza Resistance to chemical cleaning products Résistance aux produits chimiques de nettoyage Beständigkeit gegen chemische Reiniger	ISO10545-13	DISPONÍVEL Available Disponibile Erhältlich DISPONÍVEL Available Disponibile Erhältlich Min. GB Min. GB Min. GB Mind. GB	DISPONÍVEL POR REFERÊNCIA Available per reference Disponibile par référence Erhältlich auf Anfrage CONFORME Compliant Conforme Konform
	Dilatação Térmica Linear Linear Thermal Expansion Dilatation Thermique Linéaire Lineare Wärmeausdehnung - Coeficiente de dilatação térmica linear [K ⁻¹] Coefficient of linear thermal expansion [K ⁻¹] Coefficient de dilatation thermique linéaire [K ⁻¹] Linearer Wärmeausdehnungskoeffizient [K ⁻¹]	ISO10545-8	DISPONÍVEL Available Disponibile Erhältlich	CONFORME Compliant Conforme Konform
	Resistência ao Fendilhamento Crazing Resistance Résistance au tressillage Widerstand gegen Glasurrisse	ISO10545-11	EXIGIDA Required Exigée Gefordert	RESISTENTE Resistant Résistant Festigkeit
	Resistência ao Choque Térmico Resistance to Thermal Shock Résistance au choc thermique Temperaturwechselbeständigkeit	ISO10545-9	DISPONÍVEL Available Disponibile Erhältlich	RESISTENTE Resistant Résistant Festigkeit
	Dilatação com a Humidade Moisture expansion Expansion à l'humidité Feuchtedehnung	ISO10545-10	DISPONÍVEL Available Disponibile Erhältlich	CONFORME Compliant Conforme Konform
	Libertação de Chumbo e Cádmiio Release of Lead and Cadmium Liberation de Plomb et Cadmium Blei- und Cadmiumabgabe	ISO10545-15	DISPONÍVEL Available Disponibile Erhältlich	DISPONÍVEL POR REFERÊNCIA Available per reference Disponibile par référence Erhältlich auf Anfrage